



TDAN	ISFERT	CON	IANI
IDAN		CUIV	

Temperature	Time	Pressure	Peeling	Washing
140 to 160°C	8 to 12 seconds	Good	At cold	up to 80°C



PRESENTATION

Promaflex Pu is the polyurethane vynil with slightly satin apsect, designed for thin cut.

With a **95 microns thickness**, it has a transparent and adhesive plastic base which is prefect to cut small characters.

CUT

Use a classical **"flex" blade** of 45° (or any other blade would work). The blade and the felon tape of your plotter must be in good condition. Set the pressure in the way that the plastic base is slightly marked after the peeling.

Cut always in mirror effect



POSING

After peeling, place your logo on the support to mark, with the back of the plastic base toward the operator.

- Press at 140/160°C* during 8-12 seconds
- Peel the plastic base at cold
- * For inferior time transfer, holding tests are necessary



WASHING UPTO 80°C

DOUBLE POSE

Proceed in two simple steps:

- Transfer the first colour following the transfer condition
- Peel off the plastic base at cold
- Transfer the second colour with the same transfer condition

WASHING AND IRONING

Washing and ironing on reverse side Drying machine strongly discouraged

POSING ON NYLON

Holding tests are necessary before any production on Nylon (Washing condition advised : 30°C maximum)

